



150 Dodd Street  
 Marietta, GA. 30060

## Fiberglass Square Tube Properties

The Following is a list of Properties of the basic resin systems used to Pultrude our various sizes of Square Tubes.

STR (Standard Resin) – 155°C      General Purpose Rod

### PROPERTIES OF PULTRUDED SQUARE TUBE:

PROPERTIES	UNIT	STR
Flexural Stress	psi	30,000
Flexural Modules	psi x 10 <sup>6</sup>	1.8
Tensile Stress	psi	30,000
Tensile Modules	psi x 10 <sup>6</sup>	2.5
Compressive Stress	psi	30,000
Notched IZOD Impact	Ft.-lbs./in.	25
Thermal Conductivity	BTU/sf/hr/°F/in	4
24-HR Water Absorption	% max., by wt	.60
Specific Gravity / Density	10 <sup>-3</sup> g/mm <sup>3</sup>	1.8
Arc Resistance	seconds	120
Dielectric Strength	volts/mil	200

Results obtained with this data cannot be guaranteed and final determination of the suitability of any material for use contemplated or the manner of use is the sole responsibility of the user.